

DESCRIPTION

Aerosols Anti-Slip 2400 are based on a fast drying acrylic modified short oil alkyd. The products are based on lead- and chromate free pigments and contain a special anti-slip additive.

RECOMMENDED USES

Anti-Slip 2400 should be applied on metal, concrete and wood surfaces etc. or properly prepared painted substrates. Steel should be correctly primed.

Anti-Slip 2400 are intended for small maintenance jobs or for touch-up.

Anti-Slip 2400 should be used interior/exterior in light industrial exposures where anti slip characteristics are required.

TECHNICAL DATA

Finish:	satin
Colours:	
Propellant:	butane/propane
Recommended film thickness:	25 µm dry, equals averagely 100 µm wet
Drying times: at 20°C/50% RH	
To touch:	20 minutes
To handle:	60 minutes
To recoat:	after 1 hour with itself
Full hardness:	7 days
Heat resistance:	100°C (dry heat), above 65°C discoloration may occur

COVERAGE

Theoretical: 2.5 m² per spray can at 25 µm dry

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means.

Sand intact coatings and provide a proper key for adhesion.

The surface must be clean and dry during application.

DIRECTIONS FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface.

Ensure that can is in motion when spray button is pressed to avoid runs and sags.

Apply several thin layers at a few minutes interval to achieve adequate coating thickness.

After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

APPLICATION CONDITIONS

For optimum results the relative humidity shall be below 85% and the temperature of the can above 10°C.

SAFETY Consult Safety Data Sheet and Safety Information printed on the can.

SHELF-LIFE / STORAGE CONDITIONS

3 years from date of production, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C.

Form No: 1154 BR Issue: 01-09-01 The information contained herein is given in good faith. However, since application conditions are beyond our control, neither Paco Systems nor Rust-Oleum Netherlands B.V. can assume responsibility for any risks or liabilities which may result from the use of these products. The company reserves the right to modify data without prior notice.